


CHEMICAL NAME

(3,3,3-Trifluoropropyl)trimethoxysilane [Customized]

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB® PC9731 is a fluorinated alkylsilane.

TYPICAL PHYSICAL PROPERTIES

CAS No.	429-60-7
EINECS No.	207-059-3
Formula	$C_6H_{13}F_3O_3Si$
Molecular Weight	218.25
Boiling Point	144°C [760mmHg]
Flash Point	38°C
Color and Appearance	Colorless clear liquid
Density 25/25°C	1.137
Refractive Index	1.3546
Purity:	98.0% by GC

APPLICATIONS

SiSiB® PC9731 can be used for production of Fluorosilicone fluid.

SiSiB® PC9731 can be used for production of Fluorosilicone resin.

Power Chemical IS09001 IS014001 certificated Copyright© 2008 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PC9731 SILANE

PACKING AND STORAGE

Customized product packing is 100ml, 250ml, 500ml, 1L and 5L bottle. Industrialized product packing is 210L steel drum or 1000L IBC tote.

In the unopened original container SiSiB® PC9731 has a shelf life of one year in a dry, cool,ventilation, temperature less than 30 degrees warehouse storage, away from fire.

Notes

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.

Power Chemical IS09001 IS014001 certificated Copyright© 2008 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia